

| | | P | Cu | P+Cu Min | Fe | Ni | Pb | Sn | Zn | Sb | Mn | Al | Si |
|--------------------------|----------|----------|----------|----------|------|------|------|------|------|------|-----|------|------|
| GERMANY-DIN 17657 | | | | | | | | | | | | | |
| V-CuP10 | (2.1631) | 9.5-11 | 89 Min | | 0.15 | 0.2 | 0.2 | 0.2 | 0.2 | | | | |
| VR-CuP10 | (2.1633) | 9.5-11 | 89 Min | | 0.05 | 0.1 | 0.03 | 0.05 | 0.05 | 0.01 | | | |
| DIN 8513 | | | | | | | | | | | | | |
| L-CuP8 | (2.1465) | 7.6-8.4 | Rem | | | | 0.02 | | | | | 0.01 | |
| L-CuP7 | (2.1463) | 6.7-7.5 | Rem | | | | 0.02 | | | | | 0.01 | |
| L-CuP6 | (2.1462) | 5.9-6.5 | Rem | | | | 0.02 | | | | | 0.01 | |
| JAPAN-JIS H2501 | | | | | | | | | | | | | |
| 1A 15 P Cu A | | 14.5 Min | Rem | 99.75 | 0.05 | | 0.01 | 0.01 | | | | | |
| 1B 15 P Cu B | | 14 Min | Rem | 99.75 | 0.15 | | | | | | | | |
| 2 10 P Cu | | 10-11 | Rem | 99.75 | 0.15 | | | | | | | | |
| 38 P Cu | | 8 - 9 | Rem | 99.75 | 0.15 | | | | | | | | |
| EUROPEAN STANDARD | | | | | | | | | | | | | |
| Cu P 15 A | CM217E | 13.5-15 | 84.5 Min | | 0.1 | 0.1 | 0.03 | 0.05 | 0.05 | 0.01 | 0.1 | 0.02 | 0.05 |
| Cu P 15 B | CM218E | 13.5-15 | 84 Min | | 0.1 | 0.1 | 0.1 | 0.1 | 0.1 | | | | |
| Cu P 15 C | CM219E | 13.5-15 | 83.5 Min | | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | | | | |
| Cu P 10 A | CM215E | 9.5-11 | 88.5 Min | | 0.1 | 0.1 | 0.03 | 0.05 | 0.05 | 0.01 | 0.1 | 0.02 | 0.05 |
| Cu P 10 B | CM215E | 9.5-11 | 87.5 Min | | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | | | | |
| USA-ASTM B-52 | | | | | | | | | | | | | |
| Alloy A | | 14 Min | Rem | 99.75 | 0.15 | 0.15 | | | | | | | |
| Alloy B | | 10 Min | Rem | 99.75 | 0.15 | 0.15 | | | | | | | |